



Pei Evaluation Service® is an accredited ISO Standard 17065 Product Certifier, accredited by the IAS. This **Product Evaluation Report** represents a product that **Pei ES** has Evaluated. This product has a Product Evaluation Service Agreement & Follow-up Inspection Service Agreement. This **Product Evaluation Report** in no way implies warranty for this product or relieves **United States Gypsum Company** of their liabilities for this product. This **PER** is an official document if it is within one year of the Initial or Re-Approval date.

**Initial Approval**  
November, 2008

**Re-Approved**  
August, 2018

See all **Pei ES** Listings at: [www.p-e-i.com](http://www.p-e-i.com)

### Report Owner

#### United States Gypsum Company

700 North Highway 45  
Libertyville, IL 60048

### Product

**5/8" (15.9mm) USG Securock® Firecode X**  
**1/2" (12.7mm) USG Securock® Glass-Mat**  
**Sheathing**

### Approved Manufacturing Locations

<a href="#">Atlantic Wallboard Ltd. #015</a> 30 Jarvis Lane St. John, NB E2J 0A9	<a href="#">USG Co. Plant #CGC-066</a> 55 Third Line Road, Hwy#6 Hagersville, ON NOA 1H0	<a href="#">USG Co. Plant #320</a> 13425 210th Street Mediapolis, IA 52637
<a href="#">USG Co. Plant #225</a> 6825 Evergreen Avenue Jacksonville, FL 32208	<a href="#">USG Co. Plant #861</a> 1 USG Road Sweetwater, TX 79556	<a href="#">USG Co. Plant #833</a> 5500 Quarantine Road Baltimore, MD 21226
<a href="#">*USG Boral Drywall SFZ #775</a> P.O. Box 1524 PC 211 Salalah, Sultanate of Oman	*The product name <b>USG Boral Securock™</b> will only be manufactured from the Oman plant.	

### General Details

**5/8" (15.9mm) USG SECUROCK® Firecode X Glass-Mat Sheathing** and **1/2" (12.7mm) USG SECUROCK® Glass-Mat Sheathing** are manufactured at the plant locations shown above. The plant locations shown above have an approved Quality Control Manual to manufacture these products and are audited quarterly by *Progressive Engineering Inc. (Pei)*.

### Product Description

**5/8" (15.9mm) USG SECUROCK® Firecode X Glass-Mat** and **1/2" (12.7mm) USG SECUROCK® Glass-Mat Sheathing** are noncombustible exterior gypsum sheathing panels used under exterior claddings such as brick veneer, clapboard siding, panel siding, shingle siding, shake siding and architecturally specified EIFS. Panels are available 48-in. wide, and in standard lengths of 8-ft, 9-ft, and 10-ft, with square edges. Other sizes are available on special order. Board manufactured per the European EN 15283-1 Directive are available in 1200mm widths and 2400mm lengths with capabilities of up to 3048mm lengths.

### General Product Usage and Limitations

1. These products shall be installed in accordance with ASTM C 1280 *Standard Specification for Application of Gypsum Sheathing*, GA-253 *Application of Gypsum Sheathing*, and the requirements of USG Product Literature.
2. These products shall not be used as a nail base. Mechanical attachment of exterior claddings must be made directly to the framing.
3. **Securock®** can be installed on wood or steel framing. The maximum spacing for framing members is 24-in. o.c. The framing strength, fastener holding capacities of framing and fastener length is outside the scope of this Product Evaluation Report.
4. Fasteners shall be driven flush with the panel surface without countersinking or being deep enough to break the glass mat.
5. These products may be applied with long dimensions parallel or perpendicular to framing members except where limited by specific requirements. Sheathing orientation and fastener spacing may be governed by local code, or by the requirements of shear, wind or fire-resistance-rated construction. Consult local codes and site-specific construction documents to ensure such requirements are met for every assembly prior to construction.
6. These products shall remain in their original unopened packaging at the site and stored in an enclosed shelter providing protection from physical damage and exposure to the elements until used. Prevent these products from exposure to cascading water.
7. **USG** approves the use of pneumatic or gas-power-driven pin fasteners to attach **Securock® Glass-Mat Sheathing** to cold-formed steel framing, provided the pin manufacturer has evaluated **Securock®** with the pin fastener in accordance with ICC-ES AC259 Acceptance Criteria, and where permitted by local codes.
8. The **1/2" (12.7mm) Securock®** and **5/8" (15.9mm) Securock® Firecode X Glass Mat Sheathing** can also be produced in accordance with the European Standard EN15283-1 for Gypsum Boards with Fibrous reinforcements when shipping to European nations. This directive applies to board manufactured out of the Mediapolis, IA and Baltimore, MD plants.

**Code Compliance****5/8" (15.9mm) USG SECUROCK® Firecode X Glass-Mat Sheathing:**

- Meets or exceeds the requirements of ASTM C 1177 Standard Specification for Glass Mat Gypsum Substrate for Use as Sheathing.
- Meets or exceeds the requirements for an Air Barrier Material when tested in accordance with ASTM E2178 and defined in the 2012 International Energy Conservation Code®.
- Meets or exceeds the requirements of the European Directive EN15283-1 Gypsum Boards with Fibrous Reinforcement, Gypsum Boards with Mat Reinforcement under the GM A1 Classification.
- Meets or exceeds the requirements of gypsum sheathing in accordance with the **2012 International Residential Code®** and the **2012 International Building Code®**.
- Non-combustible core when tested in accordance with ASTM E 136, and defined in **2012 International Building Code®** Section 703.5.2.
- Surface Burning Characteristics - Flame Spread 0 / Smoke Development 0 when tested in accordance with ASTM E 84.
- Meets Type X definition in accordance with ASTM C 1396 and ASTM C 1177 when tested in accordance with ASTM E 119.
- Exceeds 15 psi flatwise tensile bond capacity required for adhesively attached EIFS when tested in accordance with ASTM C 297.
- 5/8" (15.9mm) USG SECUROCK® Firecode X Glass-Mat Sheathing is classified by Underwriter's Laboratories, Inc. as to fire resistance, surface burning characteristics, and non-combustibility. See the UL Fire Resistance Directory for fire resistive design listings.
- CE Certified by Exova Warrington Fire for Reaction to Fire Performance in accordance with European Directive EN 13501-1:2007+A1: 2009- A1 rating.
- Listed by ICC-ES, Evaluation Report ESR-3044 for compliance with 2006 & 2009 International Building Code® & International Residential Code® for Structural, Non-combustibility, Surface Burning Characteristics, Fire-Resistance-Rated construction, and Physical Properties.
- Approved by City of Los Angeles Research Report RR 25748 as to compliance with the 2011 Los Angeles Building Code.
- Approved by State of Florida Product Approval FL 11429 as to compliance with the 2010 Florida Building Code for use outside High Velocity Hurricane Zones (HVHZ).
- Approved by Miami-Dade County Notices of Acceptance (NOA) for use as a substrate in specific EIFS clad wall & protected direct-applied soffit assemblies constructed within areas designated High Velocity Hurricane Zones (HVHZ). Visit the Miami-Dade County product Control Division website for approved assemblies.

**1/2" (12.7mm) USG SECUROCK® Glass-Mat Sheathing:**

- Meets or exceeds the requirements of ASTM C 1177 Standard Specification for Glass Mat Gypsum Substrate for Use as Sheathing.
- Meets or exceeds the requirements for an Air Barrier Material when tested in accordance with ASTM E2178 and defined in the 2012 International Energy Conservation Code®.
- Meets or exceeds the requirements of the European Directive EN15283-1 Gypsum Boards with Fibrous Reinforcement, Gypsum Boards with Mat Reinforcement under the GM A1 Classification.
- Meets or exceeds the requirements of gypsum sheathing in accordance with the **2012 International Residential Code®** and the **2012 International Building Code®**.
- Non-combustible core when tested in accordance with ASTM E 136, and defined in **2012 International Building Code®** Section 703.5.2.
- Surface Burning Characteristics - Flame Spread 0 / Smoke Development 0 when tested in accordance with ASTM E 84.
- Exceeds 15 psi flatwise tensile bond capacity required for adhesively attached EIFS when tested in accordance with ASTM C 297.
- Meets the requirements of a thermal barrier as defined by **2012 International Building Code®** Section 2603.4.
- CE Certified by Exova Warrington Fire for Reaction to Fire Performance in accordance with European Directive EN 13501-1:2007+A1: 2009- A1 rating.
- Listed by ICC-ES, Evaluation Report ESR-3044 for Compliance with 2006 & 2009 International Building Code® & International Residential Code® for Structural, Non-combustibility, Surface Burning Characteristics, Fire-Resistance-Rated construction, and Physical Properties.
- Approved by City of Los Angeles Research Report RR 25748 as to compliance with the 2011 Los Angeles Building Code.
- Approved by State of Florida Product Approval FL 11429 as to compliance with the 2014 Florida Building Code for use outside High Velocity Hurricane Zones (HVHZ).
- Approved by Miami-Dade County Notices of Acceptance (NOA) for use as a substrate in specific EIFS clad wall & protected direct-applied soffit assemblies constructed within areas designated High Velocity Hurricane Zones (HVHZ). Visit the Miami-Dade County product Control Division website for approved assemblies.

**Tables and Design Values**

**Table 1 - Physical Properties per ASTM C1177**

Flexural Strength (ASTM C473-06)	1/2" Securock® Glass-Mat Sheathing	5/8" Securock® Glass-Mat Sheathing
<b>Minimum Breaking Load</b>		
Edge Perpendicular	107 lbf	147 lbf
Edge Parallel	80 lbf	100 lbf
<b>Hardness (lbf)</b>		
Core Test	15 min	15 min
End Test	15 min	15 min
Edge Test	15 min	15 min
<b>Nail Pull Resistance</b>	80 min	90 min
<b>Water Absorption (% by weight)</b>	10% max	10% max
<b>Surface Burning</b>	0/0	0/0

**Table 2 - Design Shear Loads for USG Securock® Attached to Wood Framing**

Sheathing	Framing	Maximum Height to Width Aspect Ratio	Fastener	Fastener Spacing Inches O.C. (Perimeter and Field)	Design Shear
1/2" Securock Parallel to Framing	16" o.c.	1:1	#6-18 Bugle head Screw	4 and 8	123.4 plf
1/2" Securock Parallel to Framing	16" o.c.	1:1	Hot Dipped Galv. Roofing Nail	4 and 8	122.0 plf
5/8" Securock Parallel to Framing	24" o.c.	1:1	#6-18 Bugle head Screw	4 and 8	138.1 plf
5/8" Securock Parallel to Framing	24" o.c.	1:1	Hot Dipped Galv. Roofing Nail	4 and 8	148.3 plf

**Notes:**

- #6 Screws must have a minimum head dia. of .325"
- Roofing Nails must have a minimum head dia. of .372"
- The perimeter of the sheathing must be supported by framing members.
- The Nails & Screws must have a minimum edge distance of 3/8"
- Framing to be nominal 2 x4 No.1 Grade S.Y.P. minimum, 24"o.c. or less
- Allowable shear values are for short term wind loads
- Shear wall anchorage is outside of the scope of this report

**Table 3 - USG 5/8" Securock® Firecode X & USG 1/2" Securock® Glass-Mat Sheathing Thermal Resistance Values per ASTM C 518**

Thickness (in.)	Thickness (mm)	R (K·M <sup>2</sup> /W)	R (°F·ft <sup>2</sup> ·h/BTU)
1/2" (12.7mm)	12.9	0.079	0.45
5/8" (15.9mm)	16.3	0.088	0.50

**Table 4 - USG 5/8" Securock® Firecode X & USG 1/2" Securock® Glass-Mat Sheathing**

<b>Water Vapor Transmission Rate per ASTM E 96</b>	
Thickness	Average
1/2" (12.7mm)	29.7
5/8" (15.9mm)	28.5

**Table 5 - Physical Properties per European Directive EN 15283-1**

	12.7mm Securock® Glass-Mat Sheathing		15.9mm Securock® Glass-Mat Sheathing	
	Min	Max	Min	Max
Nominal Thickness	12.4	13	15.8	16.6
Width	1200	1200	1200	1200
Length	2400	3048	2400	3048
<b>Minimum Breaking Load (N)</b>				
	Min	Max	Min	Max
Longitudinal	533.0	--	679.0	
Transverse	356.0	--	445.0	
Water Absorption (% by weight)	10% max		10% max	
Reaction to Fire	A1		A1	

**Table 6 - Design Loads for Negative or Positive Transverse Wind Load**

Sheathing	Frame Spacing	Fastener	Sheet Direction	Fastener Spacing Inches O.C. (Perimeter and Field)	Design Load (psf)
<b>1/2"</b> Securock	16" o.c.	2" Hot Dipped Galv. Roofing Nail	Vertical	8 and 8	<b>30.0</b>
<b>1/2"</b> Securock	16" o.c.	#6 x 1-1/4 Bugle head Screw	Horizontal	8 and 8	<b>32.3</b>
<b>1/2"</b> Securock	16" o.c.	#6 x 1-1/4 Bugle head Screw	Vertical	8 and 8	<b>26.7</b>
<b>1/2"</b> Securock	24" o.c.	#6 x 1-1/4 Bugle head Screw	Vertical	8 and 8	<b>16.0</b>
<b>5/8"</b> Securock	12" o.c.	#6-18 Bugle head Screw	Vertical	4 and 4	<b>107.3</b>
<b>5/8"</b> Securock	16" o.c.	1-5/8" Buglehead Drywall Screw	Vertical	8 and 8	<b>38.7</b>
<b>5/8"</b> Securock	16" o.c.	1-3/4" Hot Dipped Galv. Roofing Nail	Vertical	8 and 8	<b>45.2</b>
<b>5/8"</b> Securock	24" o.c.	1-3/4" Hot Dipped Galv. Roofing Nail	Vertical	8 and 8	<b>23.1</b>
<b>5/8"</b> Securock	24" o.c.	1-5/8" Buglehead Drywall Screw	Vertical	4 and 4	<b>34.4</b>
<b>5/8"</b> Securock	24" o.c.	1-5/8" Buglehead Drywall Screw	Vertical	6 and 6	<b>27.2</b>
<b>5/8"</b> Securock	24" o.c.	1-5/8" Buglehead Drywall Screw	Horizontal	8 and 8	<b>29.0</b>
<b>5/8"</b> Securock	24" o.c.	1-5/8" Buglehead Drywall Screw	Vertical	8 and 8	<b>25.2</b>

**Notes:**

1. The sheathing can be installed perpendicular or parallel to the framing.
2. The perimeter of the sheathing must be supported by framing members, except edges when installed perpendicular.
3. #6 x 1-1/4" Buglehead Screws with a minimum head dia. of .325"
4. Buglehead Drywall Screws with an average head dia. of .372"
5. The Nails & Screws must have a minimum edge distance of 3/8"
6. Allowable values are for short term wind loads.
7. The values in this table are based on testing per ASTM E330 and represent the ultimate capacity of the sheathing to resist fastener pull-through and/or flexural failure using a 3.0 Safety Factor. The withdrawal resistance of fasteners from framing is different on several factors including but not limited to fastener type, fastener length and framing properties. The specification of fasteners is the responsibility of the designer of record.
8. Framing and bracing are beyond the scope of this evaluation report

**Product Labeling**

Each panel of **Securock®** and **Securock® Firecode X Glass-Mat Sheathing** that is covered by this **PER**, must be marked with the following information:

1. **USG** Name
2. Product Name
3. Plant Identifier & Date Code
4. This **PER** Number & **Pei Evaluation Service®** Name or Logo (See Acceptable Evaluation Marks for Details)
5. UL Backstamp Information for Fire Resistance (5/8" Only)
6. Approval by City of Los Angeles Research Report RR 25748 (where applicable)
7. ICC-ES ESR-3044 (where applicable)
8. Florida Product Approval FL-11429 (where applicable)
9. Miami Dade County Notice of Acceptance (where applicable)
10. European CE Mark (Baltimore, Mediapolis plants)

**Acceptable Evaluation Marks****Test Standards**

**ASTM C 1177/C 1177M-06** - Standard Specification for Glass-Mat Gypsum Substrate for Use as Sheathing.

**ASTM C 297-04** - Standard Test Method for Flatwise Tensile Strength of Sandwich Constructions.

**ASTM C 518-04** - Standard Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus.

**ASTM D136-04** - Standard Test Method for Behavior of Materials in a Vertical Tube Furnace at 750° C.

**ASTM E 84-07** - Standard Test Method for Surface Burning Characteristics of Building Materials.

**ASTM E 96-05** - Standard Test Methods for Water Vapor Transmission of Materials.

**ASTM E 72-05** - Standard Test Methods of Conducting Strength Tests of Panels for Building Construction; Section 14 Racking Load - Evaluation of Sheathing Materials on a Standard Wood Frame.

**ASTM E 72-05** - Standard Test Methods of Conducting Strength Tests of Panels for Building Construction; Section 15 Racking Load - Evaluation of Sheathing Materials (Wet) on a Standard Wood Frame.

**ASTM E 119-00a** - Standard Methods of Fire Endurance Tests of Building Construction and Materials

**ASTM E 330-02** - Standard Test Methods for Structural Performance of Exterior Windows, Doors, Skylights and Curtain Walls by Uniform Static Air Pressure Difference

**UL 1715** - Fire Test of Interior Finish Materials.

**EN 13501-1:2007+A1: 2009** - Classification of Reaction to Fire Performance by Exova Warringtonfire.

**BS EN ISO 1716:2002** - Determination of the Heat of Combustion for Building Products by Exova Warringtonfire.

**BS EN ISO 1182:2010** - Reaction to Fire Tests for Building Products - Non Combustibility.

**Evaluated To**

European Directive EN 15283-1

**Product Documentation**

A Product Evaluation Service Agreement between **Pei Evaluation Service®** and **United States Gypsum Company**

A Follow-up Inspection Service Agreement between **Progressive Engineering Inc.** and **United States Gypsum Company**

A Quality Control Manual **USG & CGC** Gypsum Wallboard Manufacturing Facilities - Dated: 5/8/2018

A Quality Control Manual **USG** Boral Securock™ Firecode® X Glass-Mat Sheathing & **USG** Boral Securock™ Glass-Mat Sheathing - Dated: 10/26/2017

Irving Wallboard - Atlantic Wallboard, LLC - Quality Manual - Dated: 6/29/2017

Irving Wallboard Standard Operating Procedures.

**USG** Securock® Glass-Mat Sheathing Installation Instructions (WB2451) - Dated: 5/2015

**USG** Securock® Glass-Mat Sheathing Submittal Sheet (WB2452) - Dated: 6/2015

SDS for Securock® Firecode® Core Glass-Mat Sheathing Panels - 54000004003 - Dated: 3/24/2017

SDS for Securock® Glass-Mat Sheathing Panels - 54000004002A - Dated: 3/24/2017



**Product Documentation Continued**

A *Pei* test report No. 2008-0430 (A) - Evaluation of the 5/8" **USG Securock® Firecode X Glass-Mat Sheathing** - Dated: 4/22/2008 - Stamped by a professional engineer.

A *Pei* test report No. 2008-0430 (B) - ASTM E96 Water Vapor Transmission Test on 5/8" **USG Securock® Firecode X Glass-Mat Sheathing** - Dated: 4/3/2008 - Stamped by a professional engineer.

A *Pei* test report No. 2008-0430 (C) - ASTM C297 Flatwise Tensile Strength Tests on 5/8" **USG Securock® Firecode X Glass-Mat Sheathing** with a Cement Base Coat and an Acrylic Base Coat - Dated: 7/28/2008 - Stamped by a professional engineer.

Intertek Test Report 3152720SAT-001 - ASTM C518-04 - Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of The Heat Flow Meter Apparatus - Dated: 5/29/2008.

UL Test Report 08CA05819 - Tests in accordance with ASTM E84-07 - Test for Surface Burning Characteristics of Building Materials - Dated: 5/21/2008 - Stamped by a Professional Engineer.

UL Test Report 08CA05754 - Tests in accordance with ASTM E119-03 - Fire Tests of Building Construction and Materials - Revised: 5/14/2009 - Stamped by a Professional Engineer.

A *Pei* test report No. 2008-1099 (A) - Evaluation of the 1/2" **USG Securock® Glass-Mat Sheathing** to ASTM C1177/C1177 M-06 - Dated: 10/16/2008 - Stamped by a professional engineer.

A *Pei* test report No. 2008-1099 (B) - ASTM E96 Water Vapor Transmission Test on 1/2" **USG Securock® Glass-Mat Sheathing** - Dated: 11/07/2008 - Stamped by a professional engineer.

A *Pei* test report No. 2008-1099 (D) - ASTM E72 Evaluation of Sheathing Materials - Single Sided Racking Load Using Dry 1/2" **USG Securock® Glass-Mat Sheathing Mechanically Fastened to Wood Framing Using Screws** - Dated: 10/16/2008 - Stamped by a professional engineer.

A *Pei* test report No. 2008-1099 (E) - ASTM E72 Evaluation of Sheathing Materials - Single Sided Racking Load Using Wet/ReDry 1/2" **USG Securock® Glass-Mat Sheathing Mechanically Fastened to Wood Framing Using Screws** - Dated: 11/04/2008 - Stamped by a professional engineer.

A *Pei* test report No. 2008-1099 (F) - ASTM E72 Evaluation of Sheathing Materials - Single Sided Racking Load Using Dry 1/2" **USG Securock® Glass-Mat Sheathing Mechanically Fastened to Wood Framing Using Nails** - Dated: 10/15/2008 - Stamped by a professional engineer.

A *Pei* test report No. 2008-1099 (G) - ASTM E72 Evaluation of Sheathing Materials - Single Sided Racking Load Using Wet/ReDry 1/2" **USG Securock® Glass-Mat Sheathing Mechanically Fastened to Wood Framing Using Nails** - Dated: 10/28/2008 - Stamped by a professional engineer.

A *Pei* test report No. 2008-1099 (H) - ASTM E330 Negative Wind Load Test on Dry 1/2" **USG Securock® Glass-Mat Sheathing on Lumber Framing** - Dated: 10/20/2008 - Stamped by a professional engineer.

A *Pei* test report No. 2008-1099 (I) - ASTM E330 Negative Wind Load Test on Dry 1/2" **USG Securock® Glass-Mat Sheathing on Lumber Framing** - Dated: 10/20/2008 - Stamped by a professional engineer.

A *Pei* test report No. 2008-1099 (J) - ASTM E330 Negative Wind Load Test on Dry 1/2" **USG Securock® Glass-Mat Sheathing on Lumber Framing** - Dated: 10/28/2008 - Stamped by a professional engineer.

A *Pei* test report No. 2008-1099 (K) - ASTM E330 Negative Wind Load Test on Dry 1/2" **USG Securock® Glass-Mat Sheathing on Lumber Framing** - Dated: 10/15/2008 - Stamped by a professional engineer.

A *Pei* test report No. 2008-1853 (A) - ASTM E72 Evaluation of Sheathing Materials - Single Side Racking Load using Dry 5/8" **USG Securock® Firecode X Glass-Mat Sheathing Mechanically Fastened to Wood Framing Using Nails** - Dated: 12/23/2008 - Stamped by a professional engineer.

A *Pei* test report No. 2008-1853 (B) - ASTM E72 Evaluation of Sheathing Materials - Single Side Racking Load using Wet/ReDry 5/8" **USG Securock® Firecode X Glass-Mat Sheathing Mechanically Fastened to Wood Framing Using Nails** - Dated: 12/30/2008 - Stamped by a professional engineer.

A *Pei* test report No. 2008-1853 (C) - ASTM E72 Evaluation of Sheathing Materials - Single Side Racking Load using Dry 5/8" **USG Securock® Firecode X Glass-Mat Sheathing Mechanically Fastened to Wood Framing Using Screws** - Dated: 12/23/2008 - Stamped by a professional engineer.

A *Pei* test report No. 2008-1853 (D) - ASTM E72 Evaluation of Sheathing Materials - Single Side Racking Load using Wet/ReDry 5/8" **USG Securock® Firecode X Glass-Mat Sheathing Mechanically Fastened to Wood Framing Using Screws** - Dated: 12/29/2008 - Stamped by a professional engineer.

A *Pei* test report No. 2008-1853 (E) - ASTM E330 Negative Windload Test on Dry 5/8" **USG Securock® Firecode X Glass-Mat Sheathing Vertical on 16" o.c. Lumber Framing Using Screws** - Dated: 12/16/2008 - Stamped by a professional engineer.

A *Pei* test report No. 2008-1853 (F) - ASTM E330 Negative Windload Test on Dry 5/8" **USG Securock® Firecode X Glass-Mat Sheathing Horizontal on 24" o.c. Lumber Framing Using Screws** - Dated: 12/18/2008 - Stamped by a professional engineer.

A *Pei* test report No. 2008-1853 (G) - ASTM E330 Negative Windload Test on Dry 5/8" **USG Securock® Firecode X Glass-Mat Sheathing Vertical on 24" o.c. Lumber Framing Using Screws** - Dated: 12/19/2008 - Stamped by a professional engineer.

**Product Documentation continued**

A *Pei* test report No. 2008-1853 (J) - ASTM C297 Flatwise Tensile Strength Tests on 1/2" USG Securock® Glass-Mat Sheathing With a Cement Base Coat and an Acrylic Base Coat- Dated: 1/14/2009 - Stamped by a professional engineer.

A *Pei* test report No. 2008-1853 (K) - ASTM C297 Flatwise Tensile Strength Tests on 5/8" USG Securock® Firecode X Glass-Mat Sheathing With a Cement Base Coat and an Acrylic Base Coat- Dated: 1/14/2009 - Stamped by a professional engineer.

A *Pei* test report No. 2008-1853 (L) - ASTM E330 Negative Windload Test on Dry 5/8" USG Securock® Firecode X Glass-Mat Sheathing Vertical on 16" o.c. Lumber Framing Using Nails - Dated: 1/21/2009 - Stamped by a professional engineer.

A *Pei* test report No. 2008-1853 (M) - ASTM E330 Negative Windload Test on Dry 5/8" USG Securock® Firecode X Glass-Mat Sheathing Vertical on 24" o.c. Lumber Framing Using Nails - Dated: 1/21/2009 - Stamped by a professional engineer.

A *Pei* test report No. 2009-0863 (A) - ASTM E330 Negative Windload Test on Dry 5/8" USG Securock® Firecode X Glass-Mat Sheathing Vertical on 24" o.c. Lumber Framing Using Screws 4" o.c. - Dated: 7/17/2009 - Stamped by a professional engineer.

A *Pei* test report No. 2009-0863 (B) - ASTM E330 Negative Windload Test on Dry 5/8" USG Securock® Firecode X Glass-Mat Sheathing Vertical on 12" o.c. Lumber Framing Using Screws 4" o.c. - Dated: 7/23/2009 - Stamped by a professional engineer.

A *Pei* test report No. 2009-0863 (C) - ASTM E330 Negative Windload Test on Dry 5/8" USG Securock® Firecode X Glass-Mat Sheathing Vertical on 24" o.c. Lumber Framing Using Screws 6" o.c. - Dated: 7/23/2009 - Stamped by a professional engineer.

Intertek Test Report 3164994SAT-001a - ASTM C518-04 - Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of The Heat Flow Meter Apparatus - Dated: 11/04/2008.

UL Test Report 09CA06340 - ASTM E84-08 - Tests in accordance with ANSI/UL 723 - Surface Burning Characteristics of Building Materials - Dated: 5/29/2009 - Stamped by a Professional Engineer.

ASTM E119-00a - Fire Tests of Building Construction and Materials - Dated: 5/29/2009 - Stamped by a Professional Engineer

UL 1715 - Standard Fire Test of Interior Finish Materials - Dated: 5/29/2009 - Stamped by a Professional Engineer

ASTM E84-07 - Fire Tests For Surface Burning Characteristics of Building Materials - Dated: 5/29/2009 - Stamped by a Professional Engineer

Tests in accordance with a combustion behavior test conducted in accordance with the standard, Behavior of Materials in a Vertical Tube Furnace at 750°C - Dated: 5/29/2009 - Stamped by a Professional Engineer

ASTM D136-04 - Standard Test Method for Behavior of Materials in a Vertical Tube Furnace at 750°C - Dated: 5/29/2009 - Stamped by a Professional Engineer

Evaluation Listing from NRC-CNRC Institute for Research and Construction for compliance to the Canadian Construction Materials Guidelines, Evaluation Listing CCMC 13491-L - Dated: 02/22/2010.

Exova Warringtonfire Test Report 195538 For 1/2" & 5/8" Securock® - Classification of Reaction to Fire Performance in Accordance with EN 13501-1:2007+A1: 2009 - Dated: 9/07/2010.

Exova Warringtonfire Test Report 194045/45 For Glass Fiber Mat & Gypsum Based Core - Determination of the Heat of Combustion for Building Products - Dated: 7/19/2010.

Exova Warringtonfire Test Report 194046 For 1/2" Securock® - Determination of the Heat of Combustion for Building Products - Dated: 7/19/2010.

Exova Warringtonfire Test Report 309471 For 1/2" & 5/8" Securock® - Classification of Reaction to Fire Performance in Accordance with EN 13501-1:2007+A1: 2009 - Dated: 8/15/2011.

Exova Warringtonfire Test Report 309283 For 1/2" & 5/8" Securock® - Fire Test For Non-Combustibility of Building Products in Accordance with BS EN ISO 1182: 2010 - Dated: 7/29/2011.

ASTM E84-13 - Fire Tests For Surface Burning Characteristics of Building Materials - Dated: 7/11/2014

A *Pei* test report No. 2014-1069 (A) - ASTM C1177/C1177M-13 Nail Pull Resistance Specification Test on 5/8" USG Securock® Firecode X Glass-Mat Sheathing with Coated Atlas Mat (WT ES 9000) - Dated: 7/29/2014

A *Pei* test report No. 2014-1069 (B) - ASTM C297 Flatwise Tensile Strength Tests on 5/8" USG Securock® Firecode X Glass-Mat Sheathing with Coated Atlas Mat (WT ES 9000) - Dated: 7/30/2014

A *Pei* test report No. 2014-1069 (C) - ASTM E96 Water Vapor Transmission Tests on 1/2" and 5/8" USG Securock® Glass-Mat Sheathing with Coated Atlas Mat (WT ES 9000) Tested to Procedure A - Desiccant Method - Dated: 7/21/2014

A *Pei* test report No. 2014-1069 (D) - ASTM C297 Flatwise Tensile Strength Tests on 5/8" USG Securock® Firecode X Glass-Mat Sheathing Five (5) Sample Sets - Dated: 4/24/2015

A *Pei* test report No. 2014-1069 (E) - ASTM C297 Flatwise Tensile Strength Tests on Alternative Glass-Mat Facing Material for USG Securock® Glass-Mat Sheathing - Dated: 4/24/2015

A *Radco* test report RAD-5574 - ASTM E2178 Air Permeance of Building Materials Tests on 1/2" USG Securock® Glass-Mat Sheathing with Coated Atlas Mat (WT ES 9000) - Dated: 10/8/2014

A *Radco* test report RAD-5578 - ASTM E2178 Air Permeance of Building Materials Tests on 5/8" USG Securock® Firecode X Glass-Mat Sheathing with Coated Atlas Mat (WT ES 9000) - Dated: 10/8/2014



**Figure 1 - USG Securock® Brand Glass-Mat Sheathing Face Mat**



**Figure 2 - CGC Securock® Brand Glass-Mat Sheathing Face Mat**



**Figure 3 - USG Boral Securock® Brand Glass-Mat Sheathing Face Mat**